

Products

	G sebs	D sbs	V tpv	TPO tpo
Hardness (Shore A-D)	5 A – 65 D	20 A – 65 D	30 A – 65 D	80 A – 65 D
Density (g/cm3)	min. 0,89	min. 0,89	min. 0,90	min. 0,88
Compression Set	good	medium	very good	medium
Working Temp. Max. (°C)	130	65	140	100
Working Temp. Min. (°C)	-40	-30	-40	-40
Solvent Resistance	medium	poor	good	medium
Motor Oil Resistance	medium	poor	good	medium
Acid-Base Resistance	excellent	good	excellent	excellent
UV - Ozone Stability	excellent	medium	excellent	excellent
Consumer Goods	✓	✓	✓	✓
Construction Sales & gaskets	✓	✓	✓	
White Goods	✓		✓	✓
Automotive	✓		✓	✓
Medical & Care	✓	✓	✓	
Electrics & Electronics	✓	✓	✓	
Impact Additives	✓	✓	✓	✓
Appliances	✓	✓	✓	✓